



# Bloomer Plastics CJ Film

## Multipurpose Monolayer Adhesive Film

Bloomer Plastics creates all our Adhesive films with 100% virgin resins, assuring consistent quality from one order to the next.

Bloomer Plastics adhesive films are activated by heat, pressure, or a combination of both. Our Heat activated films maintain their integrity at working temperatures and are easier to handle in comparison to other adhesive technologies.

Adhesive **CJ Film** can adhere to a wide variety of substrates including:

- Acrylic Adhesives
- Aluminum
- Cotton
- Fiberglass
- Foams
- Galvanized Steel
- Glass
- Nonwovens
- Nylon
- Paper
- Scrims
- Wood

Material Description	BPI Adhesives CJ Film
DSC Lower Melt Point	74.5 °C 166.1 °F
DSC Upper Melt Point	110.0 °C 230.0 °F
Available Gauge	1.25 – 30.0 mil
Available Width	15" - 84" (381 - 2,133mm)

### Adhesive Film Properties

- Capable of handling deep draw applications
- Capable of RF Welding
- Maintain adhesive properties under varied environmental conditions
- Bloomer Plastics can corona treat this film upon request.

Physical Property*	Test Direction	Typical Values	Units	Test Method
Tensile Elongation	Machine Direction	475	(%)	ASTM D882-02
	Transverse Direction	575	(%)	ASTM D882-02
Tensile Strength	Machine Direction	3,400	(psi)	ASTM D882-02
	Transverse Direction	2,100	(psi)	ASTM D882-02
Tensile Modulus (1% Secant)	Machine Direction	13,000	(psi)	ASTM D882-02
	Transverse Direction	12,825	(psi)	ASTM D882-02
Elmendorf Tear Strength	Machine Direction	130	(g/mil)	ASTM D1922-00a
	Transverse Direction	145	(g/mil)	ASTM D1922-00a

\*Physical Properties measured using a 3.5 mil film.

This is a table of typical values expected for the aforementioned product only. These typical values are not to be considered a specification for these properties. Typical values cannot be considered specific rejection criteria. If definitive tear and tensile properties are a requisite for the film, a true specification can be developed and provided after sufficient production experience.

Bloomer Plastics will work with you to customize film properties to meet your application. Your custom designed, heat activated film will be created to satisfy *your* process's requirements.

Call us to discuss your specific needs. 1-800-638-0479



Registered to  
ISO 9001